

Durlon<sup>®</sup> Kammprofile gaskets have a solid metal core with concentrically serrated grooves machined into the top and bottom faces. The metal core is typically stainless steel, but it can be supplied in various metallurgies as per the customer's request.

The serrated core is covered with soft sealing material and is dependent on the service conditions of the system. Flexible graphite and expanded PTFE sealing layers are most common, but other products like HT1000<sup>®</sup> or (Extreme Temperature Gaskets) ETG's can be used as well. While providing the Durlon<sup>®</sup> Kammprofile gasket with excellent sealing properties, the soft sealing layers also fill in minor flange imperfections and protect the flange surfaces from damage.

Durlon<sup>®</sup> Kammprofile gaskets are the preferred choice for applications requiring improved performance at low seating stresses. The serrated peaks provide reduced contact area and when combined with the soft conformable sealing layers, the Durlon<sup>®</sup> Kammprofile gasket provides a virtual metal-tometal connection. They feature excellent resistance to blowout and provide superior stability for ease of handling and installation.

Durlon<sup>®</sup> Kammprofile gaskets are offered in 4 styles in each of the 2 core designs.

#### **INDUSTRY APPLICATIONS:**

- Oil & Gas
- Mining
- Power Generation
  Heavy Industrial
- Petrochemical
   Chemical Processing

## Certifications

**RoHS Reach Declaration** 

Compliant

• Pulp & Paper

# Gasket Factors m, Y psi (MPa) 4.00, 1,000 (6.70)

# **DURLON**<sup>°</sup> Kammprofile

# Serrated Flat Metal Gaskets Grooved metal gasket with covering layers

Physical Properties	
Temperature: Min Max (material dependent)	-200°C (-328°F) 1,000°C (1,832°F)
Pressure, Max, bar (psi)	414 (6,000)
pH range, Room Temp.	0-14

# **CORE MATERIALS:**

- Standard core material is 316 stainless steel with a nominal thickness of 0.125" (3mm)
- Other core materials and thicknesses are available to suit specific applications
- Core material is generally selected in an identical material to the piping system in order to reduce corrosion problems

## **FACING MATERIALS:**

- Standard facing material is flexible graphite with a nominal thickness of 0.020" (0.5mm)
- Other facing materials and thicknesses are available to suit specific applications
- Meets Shell Specification MESC SPE 85/203 & PVRC SCR Flexible Graphite Spec for FG 600 material

# SHAPES:

• Round, ovals (normal or irregular), manways, track shapes, diamonds, squares/rectangles, with ribs, etc.

# FLANGE SURFACE FINISH:

• The ideal flange surface finish for use with Kammprofile gaskets is 125-250

Warning: Durlon® gasket materials should never be recommended when both temperature and pressure are at the maximum listed. Properties and applications stated are typical. No applications should be undertaken by anyone without independent study and evaluation for suitability. Never use more than one gasket in one flange joint and never reuse a gasket. Improper use or gasket selection could cause property damage and/or serious injury. Data reported is a compilation of field testing, field service reports and/or in-house testing. While the utmost care has gone into publishing the information contained herein, we assume no responsibility for errors. Specifications and information contained within are subject to change without notice. This edition cancels and obscient all previous editions.